

TECHNICAL DATA SHEET

LARIPUR 107-90 A

GENERAL DESCRIPTION

LARIPUR 107-90 A is a high-quality polycaprolactone-based TPU. Characterized by very good hydrolysis and thermal resistance and extremely low compression set values, this product is specifically designed for the production of high-performing heavy-duty seals for a wide range of pneumatic and hydraulic applications.

TYPICAL CHEMICAL- PHYSICAL PROPERTIES

Parameter		Typical Value	Unit	Method
Density		1.18	gr/cm ³	ISO 2781
Shore Hardness		90	A	ISO 7619-1
Abrasion Loss		30	mm ³	ISO 4649
Tensile Modulus:	50%	6.2	N/mm ²	ISO 22654
	100%	7.8		
	300%	25.0		
Tensile Strength		63.1	N/mm ²	ISO 22654
Elongation at Break		505	%	ISO 22654
Tear Strength		85	N/mm	ISO 34-1
Flexural Modulus		40	N/mm ²	ISO 178
Vicat Softening Point		160	°C	ISO 306
Compression set:	70h/100°C	45	%	ISO 815-1

The above reported data do not constitute sales specifications for the material in object.

The properties reported in this Technical Data Sheet are determined on annealed, injection moulded specimens and represent the average of values obtained from a significant number of production lots.

The international standards above indicated are intended as a reference for the execution of the relative tests, whereas the choice of available options and any possible variation are detailed in our respective internal standards.

The information reported in this Technical Data Sheet are based on our current best knowledge, however, even if we guarantee the quality consistency of our LARIPUR products, we reserve the option to periodically issue updated versions of this Technical Data Sheet and respective sale specifications as well.

The extrusion grade LARIPUR are identified by a specific end code (EG, EA, AE, DP, EM, EF, EP, U, EUV or HFM). This code has to be indicated when ordering those grades.

**STORAGE AND
STABILITY**

LARIPUR 107-90 A is supplied in regular pelletized form and packaged in 25 kg bags or 500 kg and 1000 kg octabins.

LARIPUR 107-90 A must be stored in its original and sealed containers and kept in a dry and well-ventilated place, avoiding the direct sun radiation.

The shelf life of LARIPUR 107-90 A is of six months from shipment date, if stored in its original sealed packaging and in proper conditions.

SAFETY

The product is not considered dangerous, nevertheless we recommend to read the Material Safety Data Sheet before handling.

**PROCESSING
RECOMMENDATIONS**

Before processing, material needs to be dried at 80-90°C for 3 hours, preferably using a dehumidifying drier fed by air with a dew point lower than -30°C.

Suggested moulding temperature profile:

Zone	Temperature
Zone 1	205°C
Zone 2	210°C
Zone 3	215°C
Nozzle	210°C

Being affected by the type of machine used, processing conditions and downstream equipment, the suggested temperature profile has to be considered as just indicative.

Edition: 06 - 09/2022